



LABORATORIO ANALISI TESSILI

RAPPORTO DI PROVA NR.	045-0270-2002
DATA DI EMISSIONE	14.03.2002
DATA RICEVIMENTO CAMPIONI	07.03.2002
DATA ACCETTAZIONE E INIZIO PROVE	07.03.2002
DATA FINE PROVE	14.03.2002

Spett.le
Pugi R.G. srl
Via Garibaldi,33 B
51037 Montale (PT)

RAPPORTO DI PROVA

DENOMINAZIONE DEL CAMPIONE: NEMI

Determinazione della resistenza all'abrasione


UNI EN ISO 12947:2000

Abrasion resistance

Apparecchio Martindale - Mezzo abradente tela standard di lana - CT indica il numero di cicli al quale si osserva un cambiamento di aspetto valutato con la della scala dei grigi (cambiamento di tono). End-Point indica il numero di cicli al quale si verifica la rottura dei primi due elementi, fili e/o trame.

Martindale abrasion machine - Reference abradant: standard wool plain woven fabric - CT : it shows the number of cycles at which a change in the aspect is observed and evaluated on the Grey scale for colour change . END-POINT : it shows the number of cycles at wich the first two elements break, thread and/or weft.

Pressione Nominale applicata <i>Nominal applicated pressure</i>	12 Kpa
Ct a nr.3000 cicli	3
End-point Cicli Cycles	50.000



IL DIRETTORE DEL LABORATORIO

Alessandro Iozzelli



1/1

- I RISULTATI ENUNCIATI SI RIFERISCONO UNICAMENTE AI CAMPIONI RICEVUTI E NON ALLA PARTITA CHE GLI STESSI RAPPRESENTANO A MENO CHE IL PRELIEVO NON SIA STATO ESEGUITO DAL PERSONALE DEL LABORATORIO E CIÒ SIA DICHIARATO SUL CERTIFICATO.
- I CAMPIONI ANALIZZATI SI CONSERVANO PER TRE MESI.
- IL PRESENTE CERTIFICATO HA VALORE SOLO SE IN ORIGINALE O IN COPIA RECANTE TIMBRO A SECCO.

- THE ABOVE-MENTIONED RESULTS REFER ONLY TO THE SAMPLES WE HEVE TESTED AND ARE ENCLOSEING TO THIS DOCUMENT AS REFERENCE SAMPLES; WE ARE NOT LIABLE FOR ANY DIFFERENCE WICH MAY ARISE AS COMPARED TO THE LOT THEY REPRESENT AND FOR ANY STATEMENT BY THE CUSTOMER.

- ISCRIZIONE DEL DIRIGENTE DEL LABORATORIO NR.496 - COLLEGIO TOSCANO PERITI - FIRENZE.