





LAB N° 0143 L

 To PUGI RG Srl  
 Via Garibaldi, 33/B  
 51037 MONTALE (PT)

Attn of Sig.ra E. Grassi

TEST REPORT		Test report N° S.8314	Test N° 23.08950	date 09-05-2023	Pag. 1/1
<u>Sample identification</u>	Date of arrival 21-04-2023	Sample id 23.00182.03	Sample reference		
Article : TIGER Colour : 14501 Compos. : 32% WO - 26% WV - 27% PA - 15% SE					
Test	PILLING MARTINDALE				
Form and terms Test method : UNI EN ISO 12945-2-4:2021 Textiles - Determination of fabric propensity to surface pilling, fuzzing or matting - Part 2: Modified Martindale method Apparatus : MARTINDALE N° Samples : 3 N° observers : 1 Weight loaded : 415 +/- 2 g for fabrics Weight loaded : 155 +/- 2 g for knitted fabrics Material : Fabric tested Rating (1-5) : 1: Minimum value ; 5: Maximum value					
<u>Test results</u>	Test start 09-05-2023	Test end 09-05-2023	Notes		
Pilling grade at 125 revs. :4-5 Pilling grade at 500 revs. :4 Pilling grade at 1000 revs. :3 Pilling grade at 2000 revs. :3 Fuzzing grade at 125 revs. :4 Fuzzing grade at 500 revs. :3-4 Fuzzing grade at 1000 revs. :3 Fuzzing grade at 2000 revs. :3 Matting grade at 2000 revs. :5					
Measure uncertainty extended:		Signatures		CEO	
		The Textile Laboratory Manager  (Dr. Jessica Fabbro)		 (Eng. Alberto Canova)	
<small>Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Textile material sent to us and not used for testing will be retained for 40 days, while technical records will be retained for 10 years, unless otherwise requested by customer. Sample identification are provided by customer and BQT declines all responsibility. This test report can't be reproduced, except in its intirety, unless approved in writing by BQT laboratory.</small>					