





LAB N° 0143 L

 To PUGI RG Srl  
 Via Garibaldi, 33/B  
 51037 MONTALE (PT)

Attn of Sig.ra E. Grassi

TEST REPORT			Test report N° S.7723	Test N° 23.08357	date 27-04-2023	Pag. 1/1
<u>Sample identification</u>		Date of arrival 21-04-2023	Sample id 23.00182.03	Sample reference		
Article : TIGER						
Colour : 14501						
Compos. : 32% WO - 26% WV - 27% PA - 15% SE						
Test	COLOUR FASTNESS TO WET RUBBING					
Form and terms						
Test method : UNI EN ISO 105-X12:2016 Textiles. Tests for colour fastness. Colour fastness to rubbing						
Apparatus : CROCKMETER						
N.of rubs : 10						
Material : Wet cotton cloths						
Load : 9 N						
Conditioning : Minimum 4 hours at 20+/-2°C and R.H.65+/-4%						
Environment of testing : 20+/-2°C and R.H.65+/-4%						
Rating (with grey scale 1-5): 1: Maximum change and maximum stain ; 5: No change and no stain						
<u>Test results</u>	Test start 27-04-2023	Test end 27-04-2023	Notes			
Staining Longitudinal	:4/5	index				
Staining Transversal	:4/5	index				
Measure uncertainty extended:			Signatures			
			The Textile Laboratory Manager		CEO	
			 (Dr. Jessica Fabbro)		 (Eng. Alberto Canova)	
<small>Sample acclimatization and test conditions are those provided by reference regulations. Measures and test results are exclusively reported to the tested sample, as provided by customer, and they do not constitute product approval. Sampling by customer. Textile material sent to us and not used for testing will be retained for 40 days, while technical records will be retained for 10 years, unless otherwise requested by customer. Sample identification are provided by customer and BQT declines all responsibility. This test report can't be reproduced, except in its intirety, unless approved in writing by BQT laboratory.</small>						