



**LANARTEX S.r.l.**

Via I Maggio, 27  
59013 Oste - Montemurlo (PO)  
Tel.: 0574-071701 Fax: 0574-899903  
E-mail: labo@lanartex.it  
www.lanartex.it



LAB N° 0572 L

**MESSRS:  
PUGI R.G. S.R.L.**

VIALE MARCONI 50/15  
59100 PRATO (PO)  
IT

<b>REPORT NR</b>	<b>220005378-001</b>
<b>REPORT DATE</b>	<b>08/08/2022</b>
ACCEPTANCE DATE	01/08/2022
START TEST DATE	08/08/2022
END TEST DATE	08/08/2022
SAMPLING BY CUSTOMER	

## TEST REPORT

**Item Name:** ART. JUNGLA

**Material type:** Orthogonal fabric  
**Intended use:** Upholstery  
**Weight:** 395.00 g/m<sup>2</sup>

**Declared Composition:**

Wool - WO 75,0 %  
Nylon or Polyamide - PA 20,0 %  
Other Fibres - AF 5,0 %



**Technical Manager**  
Dott.ssa Guidotti Valentina

**Manager Director**  
Patrizia Rosati

(\*) = Tests and analytes marked with asterisk are not accredited ACCREDIA. The content of the present document refers **exclusively to the submitted samples** and not to the batch that they want to represent. This report is made solely on the basis of materials supplied by the customer. This test report cannot be reproduced in part without written permission of LANARTEX. The sample description content is under the full responsibility of the customer and not of the laboratory. Except when specifically stated, **the results apply to the sample as received**. For any further information, please read the General Sales Condition on the Lanartex website.



**LANARTEX S.r.l.**

Via I Maggio, 27  
59013 Oste - Montemurlo (PO)  
Tel.: 0574-071701 Fax: 0574-899903  
E-mail: labo@lanartex.it  
www.lanartex.it



LAB N° 0572 L

**REPORT NR**  
**REPORT DATE**

**220005378-001**  
**08/08/2022**

## TEST LIST

TEST	METHOD	ACCREDIA
------	--------	----------

**Flammability of fabrics - Upholstered furniture**

UNI 9175:2010 + UNI 9176:2010

*Infiammabilità dei tessuti - Mobili imbottiti*

(\*) = Tests and analytes marked with asterisk are not accredited ACCREDIA. The content of the present document refers **exclusively to the submitted samples** and not to the batch that they want to represent. This report is made solely on the basis of materials supplied by the customer. This test report cannot be reproduced in part without written permission of LANARTEX. The sample description content is under the full responsibility of the customer and not of the laboratory. Except when specifically stated, **the results apply to the sample as received**. For any further information, please read the General Sales Condition on the Lanartex website.



**LANARTEX S.r.l.**

Via I Maggio, 27  
59013 Oste - Montemurlo (PO)  
Tel.: 0574-071701 Fax: 0574-899903

E-mail: labo@lanartex.it  
www.lanartex.it



LAB N° 0572 L

**REPORT NR**  
**REPORT DATE**

**220005378-001**  
**08/08/2022**

## RESULTS

M.U.	RESULT
<b>UNI 9175:2010 + UNI 9176:2010</b>	
<b>Flammability of fabrics - Upholstered furniture</b>	
<i>Infiammabilità dei tessuti - Mobili imbottiti</i>	
<b>Pretreatment (according to UNI 9176)</b>	
<i>Pretrattamento (secondo UNI 9176)</i>	You submit samples of the test material to 200 steps of a brush with weight 15±1 g/cm <sup>2</sup> of the apparent surface of contact between the brush and the same sample Si sottopongono i campioni di materiale in esame a 200 passaggi di una spazzola con peso di 15±1 g/cm <sup>2</sup> della superficie apparente di contatto tra la spazzola stessa e il campione
<b>Kind of sample</b>	Cover material
<i>Tipo campione</i>	Tessuto esterno
<b>Filling material</b>	PU-FR (30-33 Kg/m <sup>3</sup> ) supplied by the laboratory
<i>Materiale per imbottitura</i>	PU-FR (30-33 Kg/m <sup>3</sup> ) fornito dal laboratorio di prova
<b>Test assembly 1</b>	Sample obtained with long side parallel to the longitudinal direction of the covering + filling material
<i>Assemblaggio 1</i>	Campione ricavato con lato lungo parallelo alla direzione longitudinale del rivestimento + imbottitura
<b>Test assembly 2</b>	Sample obtained with long side parallel to the transversal direction of the covering + filling material
<i>Assemblaggio 2</i>	Campione ricavato con lato lungo parallelo alla direzione trasversale del rivestimento + imbottitura
<b>Preliminary test on filling material - 20 s - Result 1</b>	Positive
<i>Esame preliminare su imbottitura - 20 s - Risultato 1</i>	Pos/Neg Positivo
<b>Preliminary test on filling material - 20 s - Result 2</b>	Positive
<i>Esame preliminare su imbottitura - 20 s - Risultato 2</i>	Pos/Neg Positivo
<b>Test assembly 1 - 20 s - Time post-combustion (combustion flame)</b>	1
<i>Assemblaggio 1 - 20 s - Tempo di post-combustione (Combustione con fiamma)</i>	s
<b>Test assembly 1 - 20 s - Time of post-glow</b>	22
<i>Assemblaggio 1 - 20 s - Tempo di Post-incandescenza</i>	s
<b>Test assembly 1 - 20 s - Result</b>	Positive
<i>Assemblaggio 1 - 20 s - Risultato</i>	Pos/Neg Positivo
<b>Test assembly 2 - 20 s - Time post-combustion (combustion flame)</b>	1
<i>Assemblaggio 2 - 20 s - Tempo di post-combustione (Combustione con fiamma)</i>	s
<b>Test assembly 2 - 20 s - Time of post-glow</b>	24
<i>Assemblaggio 2 - 20 s - Tempo di Post-incandescenza</i>	s
<b>Test assembly 2 - 20 s - Result</b>	Positive
<i>Assemblaggio 2 - 20 s - Risultato</i>	Pos/Neg Positivo
<b>Test assembly 1 - 80 s - Time post-combustion (combustion flame)</b>	7
<i>Assemblaggio 1 - 80 s - Tempo di post-combustione (Combustione con fiamma)</i>	s
<b>Test assembly 1 - 80 s - Time of post-glow</b>	37
<i>Assemblaggio 1 - 80 s - Tempo di Post-incandescenza</i>	s
<b>Test assembly 1 - 80 s - Result</b>	Positive
<i>Assemblaggio 1 - 80 s - Risultato</i>	Pos/Neg Positivo
<b>Test assembly 2 - 80 s - Time post-combustion (combustion flame)</b>	10
<i>Assemblaggio 2 - 80 s - Tempo di post-combustione (Combustione con fiamma)</i>	s

(\* ) = Tests and analytes marked with asterisk are not accredited ACCREDIA. The content of the present document refers **exclusively to the submitted samples** and not to the batch that they want to represent. This report is made solely on the basis of materials supplied by the customer. This test report cannot be reproduced in part without written permission of LANARTEX. The sample description content is under the full responsibility of the customer and not of the laboratory. Except when specifically stated, **the results apply to the sample as received**. For any further information, please read the General Sales Condition on the Lanartex website.



**LANARTEX S.r.l.**

Via I Maggio, 27  
59013 Oste - Montemurlo (PO)  
Tel.: 0574-071701 Fax: 0574-899903  
E-mail: labo@lanartex.it  
www.lanartex.it



LAB N° 0572 L

**REPORT NR**  
**REPORT DATE**

**220005378-001**  
**08/08/2022**

**Test assembly 2 - 80 s - Time of post-glow**

*Assemblaggio 2 - 80 s - Tempo di Post-incandescenza*

s 40

**Test assembly 2 - 80 s - Result**

*Assemblaggio 2 - 80 s - Risultato*

Pos/Neg **Positive**  
**Positivo**

**Test assembly 1 - 140 s - Time post-combustion (combustion flame)**

*Assemblaggio 1 - 140 s - Tempo di post-combustione (Combustione con fiamma)*

s 8

**Test assembly 1 - 140 s - Time of post-glow**

*Assemblaggio 1 - 140 s - Tempo di Post-incandescenza*

s 46

**Test assembly 1 - 140 s - Result**

*Assemblaggio 1 - 140 s - Risultato*

Pos/Neg **Positive**  
**Positivo**

**Test assembly 2 - 140 s - Time post-combustion (combustion flame)**

*Assemblaggio 2 - 140 s - Tempo di post-combustione (Combustione con fiamma)*

s 1

**Test assembly 2 - 140 s - Time of post-glow**

*Assemblaggio 2 - 140 s - Tempo di Post-incandescenza*

s 45

**Test assembly 2 - 140 s - Result**

*Assemblaggio 2 - 140 s - Risultato*

Pos/Neg **Positive**  
**Positivo**

**Classification achieved**

*Classificazione raggiunta*

**1IM**  
**1IM**

**NOTES**

The results of the following test concern only flammability characteristics of the combination of materials they constitute upholstered furniture according to the particular conditions used in the test must therefore not be used as hazard assessments potential fire of materials or products, in their intended use. Conditioning times: Cover: 48 hrs at 23±2 °C and 50±5 R.H. %. Filling: 72 hrs at 80±5 °C and 80±5 R.H. % followed by at least 48 hrs at 23±2 °C and 50±5 R.H. %. The laboratory is not liable for any deviation of the results caused by the failure to declare the test information requested from the customer.

I risultati della seguente prova riguardano esclusivamente caratteristiche di infiammabilità della combinazione di materiali che costituiscono mobili imbottiti secondo le particolari condizioni usate nella prova, non devono quindi essere utilizzati come valutazioni della pericolosità d'incendio potenziale dei materiali o dei prodotti, nella loro destinazione d'uso. Periodi di condizionamento: Rivestimento: 48 ore con temperatura di 23±2 °C e U.R. di 50±5 %. Imbottitura: 72 ore con temperatura di 80±5 °C e umidità relativa di 80±5 % seguito da almeno 48 ore con temperatura di 23±2 °C e umidità relativa di 50±5 %. Il laboratorio non risponde per eventuali scostamenti dei risultati causati dalla mancata dichiarazione delle informazioni di prova richieste al cliente.

**GENERAL NOTES**

Unrepeatable tests to exhaustion test material.

Prove irripetibili per esaurimento materiale.

-----  
**END OF REPORT**  
-----

(\*) = Tests and analytes marked with asterisk are not accredited ACCREDIA. The content of the present document refers **exclusively to the submitted samples** and not to the batch that they want to represent. This report is made solely on the basis of materials supplied by the customer. This test report cannot be reproduced in part without written permission of LANARTEX. The sample description content is under the full responsibility of the customer and not of the laboratory. Except when specifically stated, **the results apply to the sample as received**. For any further information, please read the General Sales Condition on the Lanartex website.