

Confidential Report

Our Ref: 23/61518/10/23





1066



Wira House, West Park Ring Road, Leeds, LS16 6QL, UK. Telephone: +44 (0) 113 259 1999

Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 31 October 2023

Our Ref: 23/61518/10/23

Your Ref: ---

Page: 1 of 5

Client: Pugi RG Srl

Via Garibaldi, 33B 51037 Montale Pistoria (PT) Italy

Job Title: Fire Test on One Fabric Sample

Clients Order Ref: --

Date of Receipt: 27 October 2023

Date Test Started: 31 October 2023

Description of Sample: One sample of fabric, which was referenced by the client as;

Fenice, stated to be 75WO 25PA

Work Requested: We were asked to make the following fire test:

IMO FTP Code 2010:Part 8

- * subcontracted test, UKAS accredited
- * subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited



Note: This report relates only to the items tested.



Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 31 October 2023

Our Ref: 23/61518/10/23

Your Ref:

Page: 2 of 5

Client: Pugi RG Srl

Product Description

Company Name	Pugi RG Srl	
FABRIC		
Type of Furniture, e.g., Seat, Sofa, Office Chair, etc;.	Seat, Sofa, Office Chair	
Name and/or Identification of the Product Tested	Fenice	
Materials of the Product and its Composite Ratio (i)		
Composition of Weave (ii)	75WO 25PA	
Density (Number/Inch) the Number of Threads per Inch in both warp and weft; and	25 inch warp & weft	
Yarn Number Count	Warp NM7000 weft NM 7000	
Thickness (mm)	2mm	
Mass per Unit Area (g/m²)	335	
Colour and Tone (iii)		
Method and Quantity of Fire Retardant Treatment		
FILLINGS		
Material (Name of Manufacturer, Type Designation)		
Type of Filling Material (eg. Foam, Polyester Fibre etc.)		
Weight per Unit Volume (kg/m³)		
Method and Quantity of Fire Retardant Treatment		

- Such as wool, nylon, polyester, etc.
- Such as plain, weave, twilled.
- (iii) If the product has a pattern, the representative colour shall be described.





1066



Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

31 October 2023 Date:

Our Ref: 23/61518/10/23

Your Ref:

Page: 3 of 5

Client: Pugi RG Srl

Testing to IMO FTP Code 2010: Part 8

Test for Upholstered Furniture

Conditioning

Immediately prior to testing the samples was placed in indoor ambient conditions for 72 hours and then conditioned in a standard atmosphere of 23±2°C temperature and 50±5% relative humidity for at least 16 hours.

The samples were tested in a room of volume 25m³ and 18°C.

Procedure

The samples was tested in accordance with IMO FTP Code 2010:Part 8 using ignition sources 0 and 1. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over combustion modified polyurethane foam with a density of approximately 34-36kg/m³.

Requirements

No progressive smouldering or flaming within 1 hour of the placement of the cigarette. Ignition Source 0

Ignition Source 1 All progressive smouldering and flaming to cease within 120 sec of removal of the burner tube.

Cigarette Specification (Source 0)

Dimensions (mm) 69mm x 8.0mm

Mass (g) 0.92 Smouldering Rate (mins/secs) 9m 37s







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 31 October 2023

Our Ref: 23/61518/10/23 Your Ref:

> Page: 4 of 5

Client: Pugi RG Srl

Results

Cigarette Test - Source 0

Specimen No.	1	2
Extinction Time (smouldering) (min)	DNP	DNP
Time of cover split	DNS	DNS
Melting (Yes/No)	No	No
Dripping (Yes/No)	No	No
Charring (Yes/No)	Yes	Yes
Progressive Smouldering (Yes/No)	No	No
Observations	DNP DNS	DNP DNS
Pass/Fail	PASS	PASS

Result of the Cigarette Test: Pass

Propane Flame Test – Source 1

Specimen No.	1	2
Time of Ignition (s)	5	5
Extinction time of flames after removal of burner (s)	1	2
Time to Cover Split (s)	18	19
Melting (Yes/No)	No	No
Dripping (Yes/No)	No	No
Charring (Yes/No)	Yes	Yes
Progressive smouldering (Yes/No)	No	No
Observations:		
Pass/Fail	PASS	PASS

Result of the Flame Test: Pass

Acronym

DNP – Did not propagate ES - Escalating smouldering BTE - Burnt to extremities





1066

EC – Escalating combustion DNS - Material did not split ME - Manually extinguished DNO – Did not observe time of event

Shirley® Technologies Limited. Registered Office: Wira House, West Park Ring Road, Leeds, LS16 6QL. A company registered in England & Wales with company number 04669651. VAT Number GB 816764800. BTTG® and Shirley® are trade names of Shirley Technologies Ltd. The supply of all goods and services is subject to our standard terms of business, copies of which are available on request. Our laboratories are accredited to EN ISO/IEC 17025.



Page:

Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

31 October 2023 Date:

Our Ref: 23/61518/10/23 Your Ref:

5 of 5

Client: Pugi RG Srl

Comment

In our opinion, based on the test carried out on the sample supplied; the results indicate that the sample meets the requirements according to IMO FTP Code 2010:Part 8.

Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (https://www.bttg.co.uk/about-us/decision-rules-policy/) for further information.

Uncertainty Budget

Measurements: ±2mm Timings: ±2 seconds.

Reported by:..... R Greasley, Laboratory Technician

..... P Doherty, Manager Countersigned by:.....

Enquiries concerning this report should be addressed to Customer Services.





1066