



## Technical specifications

| Test description                     | Norm   | U.o.M.                       | Values and tolerances |
|--------------------------------------|--|------------------------------|-----------------------|
| Composition                          | Direttive CE   | %                            | 100% PL RECYCLED      |
| Piece length and width               |  | lmt.                         | 55 ± 5%    1,40 ± 2%  |
| Weight                               | UNI EN 12127   | gr./m <sup>2</sup> -gr./mtl. | 280 ± 5% - 390 ± 5%   |
| Abrasion test-Martindale 12 KPA      | UNI EN ISO 12947   | turns                        | >=120.000 ± 20%       |
| Pilling - Martindale Method          | ISO 12945-2  | degree 1-5                   | 4/5 ± ½               |
| Colour Fastness crocking dry and wet | EN ISO 105X12  | degree 1-5                   | 4 ± 1                 |
| Lightfastness (Xenotest)             | EN ISO 105 B02 Scala dei blu                                     | degree 1-8                   | 6 ± 1                 |
| Maintenance washing                  | Use the vacuum-cleaner with smooth spout regularly, don't brush. |                              |                       |
| Symbols Maintenance                  | UNI 8423   |                              |                       |

### Certification:

Classe 1 IM - Test Report

BS 5852 Crib N°5 using a CM Foam 35 Kg/cu.m.

EN 1021 Part 1-2 using a CM Foam 35 Kg/cu.m.

Calif.Bull.117 June 2013

Test report, certificates and witness of the tested material are kept in the archives of Pugi.rg Srl.  
The material object of the test was taken by sample from our. normal production.



Pugi.rg srl - 51037 Montale PT via Garibaldi, 33b - Italy

Tel: +39.0573.557701 Fax: +39.0573.557705

E-mail: [info@pugirg.it](mailto:info@pugirg.it) [www.pugirg.it](http://www.pugirg.it)

made in Italy

%MODELLO%