


# BIO



## Technical specifications

Test description	Norm	U.o.M.	Values and tolerances
Composition	Direttive CE	%	100% PL RECYCLED
Piece length and width		lmt.	60 ± 5% 1,40 ± 2%
Weight	UNI EN 12127	gr./m <sup>2</sup> -gr./mtl.	300 ± 5% - 420 ± 5%
Abrasion test-Martindale 12 KPA	UNI EN ISO 12947	turns	>120.000
Pilling - Martindale Method	ISO 12945-2	degree 1-5	4/5 ± ½
Colour Fastness crocking dry and wet	EN ISO 105X12	degree 1-5	4 ± 1
Lightfastness (Xenotest)	EN ISO 105 B02 Scala dei blu	degree 1-8	6 ± 1
Maintenance washing	Use the vacuum-cleaner with smooth spout regularly, don't brush.		
Symbols Maintenance	UNI 8423		

**Acoustics/Sound absorption:** Flow Resistance according to ISO 9053-2:2020

**Certification:** Classe 1 IM - Test Report

BS 5852 Crib N°5 using a CM Foam 35 Kg/cu.m.

EN 1021 Part 1-2 using a CM Foam 35 Kg/cu.m.

Calif.Bull.117 June 2013

Test report, certificates and witness of the tested material are kept in the archives of Pugi.rg Srl.  
The material object of the test was taken by sample from our. normal production.

Pugi.rg®

Pugi.rg srl - 51037 Montale PT via Garibaldi, 33b - Italy

Tel: +39.0573.557701 Fax: +39.0573.557705

E-mail: info@pugirg.it www.pugirg.it

made in Italy

%MODELLO%