POSEIDON





OEKC

tessuto riciclabile recyclable fabric



acustico acoustic



Technical specifications

Test description		Norm	U.o.M.	Values and tolerances
Composition		Direttive CE	%	100% PL (RECYCLED SEAQUAL)
Piece length and width			lmt.	40 ± 5% 1,40 ± 2%
Weight		UNI EN 12127	gr./m ² -gr./mtl.	500 ± 5% - 700 ± 5%
Abrasion test-Martindale 12 KF	PA	UNI EN ISO 12947	turns	>100.000
Pilling - Martindale Method		ISO 12945-2	degree 1-5	4/5 ± 1/2
Colour Fastness crocking dry and wet		EN ISO 105X12	degree 1-5	4 ± 1
Lightfastness (Xenotest)		EN ISO 105 B02 Scala dei blu	degree 1-8	6 ± 1
Maintenance washing		Use the vacuum-cleaner with smooth spout regularly, don't brush.		
Symbols Maintenance		UNI 8423		
SEAQUAL				SEAQUAL Textile Certification No.: SY035WV2300305
Acoustics/Sound absorption:	Flow Resistance according to ISO 9053-2:2020			
Certification:	Classe 1 IM - Test Repo	ort		
BS 5852 Crib N°5 using a CM Foam 35 Kg/cu.m.				

EN 1021 Part 1-2 using a CM Foam 35 Kg/cu.m.

Calif.Bull.117 June 2013

Test report, certificates and witness of the tested material are kept in the archives of Pugi.rg Srl. The material object of the test was taken by sample from our. normal production.



Pugi.rg srl - 51037 Montale PT via Garibaldi, 33b - Italy Tel: +39.0573.557701 Fax: +39.0573.557705 E-mail: info@pugirg.it www.pugirg.it