

POSEIDON















Technical specifications

Norm	U.o.M.	Values and tolerances
Direttive CE	%	100% PL (SEAQUAL)
	lmt.	40 ± 5% 1,40 ± 2%
UNI EN 12127	gr./m²-gr./mtl.	500 ± 5% - 700 ± 5%
UNI EN ISO 12947	turns	>100.000
ISO 12945-2	degree 1-5	4/5 ± ½
EN ISO 105X12	degree 1-5	4 ± 1
EN ISO 105 B02 Scala dei blu	degree 1-8	6 ± 1
Use the vacuum-cleaner with sm	nooth spout regularly, do	on't brush.
UNI 8423	600 💥 🗷	A P III
		SEAQUAL Textile Certification No. SY035WV2300305
	UNI EN 12127 UNI EN ISO 12947 ISO 12945-2 EN ISO 105X12 EN ISO 105 B02 Scala dei blu Use the vacuum-cleaner with sm	Direttive CE

Acoustics/Sound absorption: Flow Resistance according to ISO 9053-2:2020

Certification: Classe 1 IM - Test Report

BS 5852 Crib N°5 using a CM Foam 35 Kg/cu.m. EN 1021 Part 1-2 using a CM Foam 35 Kg/cu.m.

Calif.Bull.117 June 2013

Test report, certificates and witness of the tested material are kept in the archives of Pugi.rg Srl. The material object of the test was taken by sample from our. normal production.



made in Italy