


Tennis



Technical specifications

Test description	Norm	U.o.M.	Values and tolerances
Composition	Direttive CE	%	100% Poliestere/Polyester
Piece length and width		lmt.	45 ± 5% - 1,57 ± 5%
Weight	UNI EN 12127	gr./m ² -gr./mtl.	340 ± 5% / 530 ± 5%
Abrasion test-Martindale 12 KPA	UNI EN ISO 12947	turns	78.000 ± 20%
Pilling - Martindale Method	ISO 12945-2	degree 1-5	5
Colour Fastness crocking dry	EN ISO 105X12	degree 1-5	4 ± 1
Lightfastness (Xenotest)	EN ISO 105 B02 Scala dei blu	degree 1-8	5 ± 1
Maintenance washing	Wash in water and soap. Alcohol and disinfectants for hospitals can be used. Don't use any solvent and petroleum distillate.		

Certification:

EN 1021 Part 1-2 using a CM Foam 35 Kg/cu.m.

Test report, certificates and witness of the tested material are kept in the archives of Pugi.rg Srl.
The material object of the test was taken by sample from our. normal production.



Pugi.rg srl - 51037 Montale PT via Garibaldi, 33b - Italy
Tel: +39.0573.557701 Fax: +39.0573.557705
E-mail: info@pugirg.it www.pugirg.it

■ ■ made in Italy

Rev.1-04/20